

HWC White Back / JR Platinum

- Heavy Weight Coated Duplex Board, White Back.
- Coat Weight: Top - 20 Bottom - 10 g/m²
- Basis Weights - 150 to 450 GSM

BOARD CONSTRUCTION



Product Top view



Product Bottom view



FEATURES:

White Lined Heavy Weight Coated White Back Board designed for attractive printing and packaging. Best brightness and gloss values for better print results and high value added applications.

USES:

For high demanding Printing and Packaging applications in the Wedding cards, Greeting Cards, Visiting Cards, Pharmaceutical Packaging, and other high value added applications.



HWC White Back / JR Platinum (Technical Specifications)

- Duplex Board, White Back, Coat Weight: 20:10 g/m²
- Basis Weights - 150 to 450 GSM

Substance (GSM)	Caliper (microns)	Bulk (cc/gms)	Taber Stiffness (gm-cm)	
			MD	CD
230	265	1.15	28	12
250	290	1.16	48	20
285	340	1.19	70	30
300	363	1.21	80	34
320	394	1.23	105	44
350	434	1.24	125	52
380	475	1.25	155	65
400	500	1.25	190	80
Tolerance: ± 3%	Tolerance: ± 5%	Tolerance: ± 5%	Tolerance: ± 10%	

Parameter	Unit	Value
Ply bond	J/m ²	130 min
smoothness	MI/min	40-80
Brightness	%	78 (±1)
Cobb Top	GSM	35-55
Cobb Bottom	GSM	35-70
Gloss at 75 deg	%	40 (± 5)
Moisture	%	6 - 8.0
IGT	Mts/sec	Min 0.7
		Tolerance: ± 3%

Please note:

1. The tolerances are based upon 95% confidence limit and on laboratory results of random samples from mill.
2. The specifications are subject to change without any prior notice.
3. Brightness value as per ISO Standard shall be 3% higher than that in TAPPI Standard.
4. Paper board Machine Deckle: 315 cms to 325 cms.

Venkraft Paper Mills Pvt Ltd., Unit – 2

Duplex Unit – Factory Address: 12th K.M., NH-7, Gopasandaram village, Kamandoddi (p.o.), Shoolagiri Union, Hosur-635109, Tamil Nadu, India.

Domestic Marketing Contacts: Email: marketing2@venkraft.com, Marketing Head (+ 91 9629606060), Tamil Nadu Coordinator (+91 8220005701, +91 8220788644, +91 7867008821).
Karnataka Coordinator (+91 7867008841,+91 8220005706, +91 7867013684, +91 7867013685).
Kerala Coordinator (+ 91 8220005706).
AP Coordinator (+91 9943332474).
Dispatch department (+91 7867008825).

Export Marketing Contacts: Email: exports@venkraft.com, Export Coordinator (+ 91 8220005701).

www.venkraft.com
