

JR Eco Steel - UnCoated

- Low Brightness, Without Coating, Grey Back Duplex Board
- Basis Weights - 150 to 450 GSM


BOARD CONSTRUCTION



Product Top View



Product Bottom View




FEATURES:

White Lined Un-Coated Packaging Chipboard designed for various low Cost applications. This board is an economical option for customers for use in non Printing applications.

USES:

For economic moderate quality packaging solution in the FMCG sector, Auto Industry, Textiles, Inner Liner of Shoe Boxes, Match Inner Shells, Inner Liner in Corrugated Boxes, Folding Box Boards – Mono Cartons etc.



JR Eco Steel - UnCoated (TECHNICAL SPECIFICATIONS)

- Low Brightness, Without Coating, Grey Back Duplex Board
- Basis Weights - 150 to 450 GSM

Substance (GSM)	Caliper (microns)	Bulk (cc/gms)	Taber Stiffness (gm-cm)	
			MD	CD
150	177	1.18	10	4
180	216	1.20	20	8
200	240	1.20	25	10
230	278	1.21	35	14
250	305	1.22	53	21
285	350	1.23	83	33
300	372	1.24	90	36
320	397	1.24	100	40
350	438	1.25	130	52
380	475	1.25	170	68
400	504	1.26	190	76
Tolerance: ±3%	Tolerance: ±5%	Tolerance:±5%	Tolerance: ±10%	

Parameter	Unit	Value
Ply bond	J/m ²	130 min
Smoothness (Bendsten)	ml/min	280-320
Brightness	%	67 (±1)
Cobb Top (60)	GSM	30-50
Gloss at 75 deg	%	6 (± 1)
Moisture	%	6.0 - 8.0
IGT	Mts/sec	Min 1.1
		Tolerance: ±3%

Please note:

1. The tolerances are based upon 95% confidence limit and on laboratory results of random samples from mill.
2. The specifications are subject to change without any prior notice.
3. Cobb is measured such that the entire testing is completed in 60 seconds and whatman filter is used for testing.

Venkraft Paper Mills Pvt Ltd., Unit – 2

Duplex Unit – Factory Address: 12th K.M., NH-7, Gopasandaram village, Kamandoddi (p.o.), Shoolagiri Union, Hosur-635109, Tamil Nadu, India.

Domestic Marketing Contacts: Email: marketing2@venkraft.com, Marketing Head (+ 91 9629606060), Tamil Nadu Coordinator (+91 8220005701, +91 8220788644, +91 7867008821).
Karnataka Coordinator (+91 7867008841,+91 8220005706, +91 7867013684, +91 7867013685).
Kerala Coordinator (+ 91 8220005706).
AP Coordinator (+91 9943332474).
Dispatch department (+91 7867008825).

Export Marketing Contacts: Email: exports@venkraft.com, Export Coordinator (+ 91 8220005701).

www.venkraft.com
